

518 Rec'd PCT/PTO 31 JUL 2001

FORM PTO-1390
(REV. 11-2000)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

163-338

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

U.S. APPLICATION NO. (If known, see 37 CFR 1.5

09/890515

INTERNATIONAL APPLICATION NO.
PCT/EP00/00757INTERNATIONAL FILING DATE
1 February 2000PRIORITY DATE CLAIMED
3 February 1999

TITLE OF INVENTION

PROCEDURE FOR PREPARING SILICA FROM CALCIUM SILICATE

APPLICANT(S) FOR DO/EO/US

Tiziana De Marco and Paolo Cementi

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☐ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 20 below concern document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98. With PTO 1449 and cited references
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☐ A FIRST preliminary amendment.
14. ☐ A SECOND or SUBSEQUENT preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
18. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☒ Other items or information: Copy of Form PCT/IPEA/416; International Search Report; Copy of the Demand; Copy of PCT/IB/308 and International Preliminary Examination Report

09/890515-0101

U.S. APPLICATION NO. 09/890515

INTERNATIONAL APPLICATION NO.
PCT/EP00/01466ATTORNEY'S DOCKET NUMBER
163-33921. ☒ The following fees are submitted:**BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)):**Neither international preliminary examination fee (37 CFR 1.482)
nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO
and International Search Report not prepared by the EPO or JPO. \$1000.00International preliminary examination fee (37 CFR 1.482) not paid to
USPTO but International Search Report prepared by the EPO or JPO \$860.00International preliminary examination fee (37 CFR 1.482) not paid to USPTO
but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00International preliminary examination fee (37 CFR 1.482) paid to USPTO
but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00International preliminary examination fee (37 CFR 1.482) paid to USPTO
and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00**ENTER APPROPRIATE BASIC FEE AMOUNT =****CALCULATIONS PTO USE ONLY**

\$ 860.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(e)).

\$

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	
Total claims	25 - 20 =	5	x \$18.00	\$ 160.00
Independent claims	2 - 3 =		x \$80.00	\$ 0
MULTIPLE DEPENDENT CLAIM(S) (if applicable)			+ \$270.00	\$ 270.00

TOTAL OF ABOVE CALCULATIONS =

\$ 1,200.00

☐ Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above
are reduced by 1/2.

\$

SUBTOTAL =

\$

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(f)).

\$

TOTAL NATIONAL FEE =

\$

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be
accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +

\$

TOTAL FEES ENCLOSED =

\$

Amount to be
refunded:

\$

charged:

\$

- a. ☒ A check in the amount of \$ 1,200.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. _____ in the amount of \$ _____ to cover the above fees.
A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
overpayment to Deposit Account No. 08-1540. A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card
information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

**NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR
1.137 (a) or (b)) must be filed and granted to restore the application to pending status.**SEND ALL CORRESPONDENCE TO:
JAMES V. COSTIGAN, ESQ.

HEDMAN & COSTIGAN, P.C.

1185 AVENUE OF THE AMERICAS, SUITE 2003

NEW YORK, NY 10036-2646

212-302-8989

SIGNATURE

JAMES V. COSTIGAN

NAME

25,669

REGISTRATION NUMBER

"Procedure for preparing silica from calcium silicate."

This invention concerns a procedure for preparing amorphous silica from calcium silicate.

5 From the literature, many methods are known for obtaining amorphous silica from various materials. The starting materials used are generally silicates of alkaline metals, preferably sodium, as described for example in WO96/30301.

10 A particularly interesting starting material is calcium silicate.

Natural or artificial calcium silicates are low-cost materials which, by means of the reaction of CO_2 in water, allow solid mixtures of SiO_2 and CaCO_3 to be
15 obtained, products with a high added value.

However, the use of calcium silicates instead of silicates of alkaline metals, or particularly instead of sodium silicate, presents considerable problems due to the poor solubility of calcium silicate in water, in
20 comparison with sodium silicate.

An example of a procedure for obtaining silica and compounds of silica and calcium carbonate from calcium silicates is described in patent CA 1,122,779. That patent describes a procedure for obtaining silica, in

09890515, 03401

09890545-073401 TOTAL 58860

which the calcium silicate crystals are placed in contact with CO_2 in the presence of water and converted into silica, having the same configuration as crystals of silicate, and into particles of calcium carbonate 5 attached to the particles of amorphous silica. The SiO_2 - CaCO_3 mixture is not separable and so, to recover the silica, a treatment with mineral acids is carried out. The acid decomposes the calcium carbonate into CO_2 and calcium salts. The acid may be HCl , for example, thus 10 obtaining CO_2 and calcium chloride. It is then washed with water to eliminate the calcium salt, thus obtaining an aqueous suspension containing silica. However, with a procedure of this type the quantity of silica obtained is extremely low in comparison with the volumes of liquid 15 involved. There is therefore a low production rate per unit volume, which considerably penalises the process described even though it allows particularly pure silica to be obtained.

Moreover this procedure requires the use of an inorganic 20 acid and it is not possible to recover the CaCO_3 .

The aim of this invention is therefore to develop a procedure for obtaining amorphous silica from calcium silicate which presents high yield and a high production rate, along with high purity of the product.

A further aim of this invention is to obtain a process with a low degree of environmental pollution, since instead of mineral acids it uses CO_2 alone as the acid agent. A further aim of this invention is to recover
5 precipitate calcium carbonate in mild temperature and pressure conditions.

The aim of this invention is therefore a procedure for preparing amorphous silica comprising the following phases:

- 10 a) reaction of a calcium silicate with CO_2 in an aqueous environment with the formation of a suspension **1** of agglomerated particles of SiO_2 and CaCO_3 ;
- b) treatment of the suspension **1** with a compound of aluminium, boron or zinc or mixtures of the same in a
15 neutral or basic environment, and formation of a solid phase **2** in a solution **3** containing particles of SiO_2 with nanometric dimensions;
- c) separation of the solid phase **2** from the solution **3**; and
- 20 d) treatment of the solution **3** according to one of the following methods;
- e) precipitation or drying;
- f) gelation.

In the description and the claims of this invention the

09690515-073101

expression "amorphous silica" means non crystalline silica which may be obtained in the form of a gel or in the form of a precipitate.

The reaction of phase a) of the process is carried out in an autoclave at a pressure between 0.3 MPa and 3 MPa and at a temperature between 10°C and 100°C. More particularly the phase a) is carried out at a pressure between 1.0 and 2.5 MPa and at a temperature between 15 and 40°C. Preferably the pressure is equal to 2 MPa and the temperature is equal to 20°C or 30°C.

The pH is a function of the CO₂ pressure and, around a pressure of 2 MPa, it stabilises around the value 5.2. The water/calcium silicate weight ratio may have any value, preferably between 16 and 6.4.

In these conditions of temperature, reagent concentration, pressure and pH, the reaction proceeds with the dissolution of the calcium silicate and concludes with the formation of an aqueous suspension of agglomerated particles of SiO₂ and CaCO₃.

The simultaneous precipitation of SiO₂ and CaCO₃ could be avoided by carrying out the reaction with low loads of calcium silicate (water/calcium silicate weight ratio greater than 16), obtaining a precipitate composed prevalently of CaCO₃ in the presence of a solution

containing nanometric particles of silica. In this system, however, the quantity of silica in the solution would be too low and therefore not sufficient for an industrial realisation of the process.

5 Even if the load of silica were increased, the concentration of silica in the solution would not exceed 10 kg/m³ (± 4); moreover in these experimental conditions this solution is a metastable phase which tends to gel quickly, preventing the separation of the silica from the
10 precipitated solid composed of CaCO₃.

It is known from the literature that the stabilising of a solution containing amorphous silica in particles is a function of the increase of the pH up to alkaline values ≥ 9.5 or of the reduction of the concentrations of
15 alkaline ions (R.K. Iler, The Chemistry of Silica, 1979). Alkaline pH values may be easily obtained by adding, for example, NaOH, while the problem of reaching higher concentrations of silica in the aqueous phase is more difficult to solve.

20 In order to solve this problem, the procedure according to this invention is characterised by the phase b), that is the reaction of the aqueous suspension 1, coming from the acid dissolution, with a compound of aluminium, boron or zinc or mixtures of the same in a neutral or basic

09890515-073401
TOTEL 20 57506860

environment.

The neutral or basic environment ($\text{pH} \geq 7$) is preferably realised using a solution of hydroxides or salts of alkaline metals or alkaline earth metals. In particular, 5 the solution is an aqueous solution of hydroxides of alkaline metals or alkaline earth metals and, even more particularly, the solution is an aqueous solution of sodium hydroxide.

The compound of aluminium, boron or zinc is preferably a 10 salt chosen among aluminates, borates or zincates. In particular, the salt is an alkaline aluminate or an alkaline earth aluminate and, even more preferably, the salt is a sodium aluminate.

The treatment in phase b) is decisive for the development 15 of the entire process, being essential for the separation of silica from carbonate.

This reaction allows the modification of the silica surface and the increase of its concentration in the solution 3 at least up to 50-60 kg/m³.

20 The solution 3 which forms in phase b) contains particles of silica of with nanometric dimensions defined as "primary particles". In particular the dimensions of the primary particles are between 1 and 100 nanometers.

The third phase c) of the process includes the separation

09690515-073101
TOTAL 50860

of the solid phase **2** rich in calcium carbonate from the solution **3** containing silica.

The separation phase c) is carried out by means of any of the known methods for phase separations, preferably it is done by centrifugation; if the separated solid mixture still contains silica aggregated with carbonate, it may be recycled and again subjected to the treatment with aluminate.

The fourth phase d) of the process contemplates treatment of the solution **3** containing silica, according to one of the following methods:

according to the first method, indicated as e), the treatment may be carried out preferably by drying or precipitation, obtaining precipitated silica.

Precipitation may come about by means of variation of the chemical-physical parameters, with or without the addition of precipitating agents.

In particular, precipitation may come about with the addition of CO₂, at environment pressure and temperature.

Afterwards there is the separation of the phases that formed during the precipitation phase. In particular, this separation may be achieved by means of filtration.

The solid kept back by the filter is washed until a neutral pH (about 7) is reached in the washing waters.

09990543-07101

According to the method f), the treatment leads to gelation, followed by evaporation of the liquid phase. The gelation treatment, as known in the art, is achieved by acidification, for example by adding CO₂, at
5 environment temperature, to a pH lower than 7. Depending on the temperature at which evaporation takes place, cryogel, aerogel or xerogel may be obtained.

It is to be noted that the first phase of the process (reaction of calcium silicate with CO₂) and the second
10 phase of the process (treatment with salts containing aluminium, boron or zinc) may also be simultaneous and carried out in the same reactor, adequately checking the pH with suitable buffers.

A further aim of this invention is the use of the
15 amorphous silica obtained with the procedure according to this invention as an additive in mixtures for tyres with low rolling resistance force or as a mineral addition in High Performance Concretes (HPC), such as high or very high strength concrete (preferably more than 100 MPa).

20 The term High Performance Concretes (HPC) identifies a class of cement mixes with characteristics of high mechanical strength (compression strength R_c at 28 days greater than 60 MPa).

An example of HPC is a high-strength concrete known as

0980515-070
FOI 2015-0506860

DSP (densified with small particles). In this material the microstructure of the cement matrix is densified by adding silica fume. In DSP it is possible to reach R_c at 28 days greater than 100 MPa.

- 5 In particular, also the compound material composed of the mixture of silica and calcium carbonates, obtained according to the procedure of this invention, may be used directly as an additive in mixtures for tyres or in high-performance concretes, for example in a high-strength
10 concrete (DSP).

Moreover the amorphous silica obtained with the procedure according to this invention may be used in many other sectors; it may be used as a reinforcing load in rubber and other organic polymers, as a pigment partially
15 substituting TiO_2 in the production of paper and coating, as a dimmer in the water paint and varnishes industry, as a thinner in solid formulations, as an anti-blocking agent to prevent adhesion between smooth surfaces, as an anti-binding agent or a catalytic support.

- 20 The principal advantage of the procedure according to this invention is that of obtaining high-purity amorphous silica by means of a process with a low environmental impact, presenting high production rate and high yield at the same time.

A further advantage of this invention is that of obtaining precipitated calcium carbonate in the form of fine particles.

The starting material may be natural, synthetic,
5 crystalline and amorphous calcium silicates.

The starting material may also be clinker of Portland cement. By clinker of Portland cement is meant a hydraulic material which must be composed of at least two thirds in mass of calcium silicates ($3\text{CaO} \cdot \text{SiO}_2$) and
10 ($2\text{CaO} \cdot \text{SiO}_2$). The remaining part contains aluminium oxide (Al_2O_3), ferric oxide (Fe_2O_3) and other oxides. The CaO/SiO_2 mass ratio must not be less than 2.0. The magnesium oxide (MgO) content must not exceed 5.0% of the mass.

15 Clinker of Portland cement is obtained by the baking, at least as far as sintering, of a precisely established mixture of raw materials (raw meal, paste or suspension) containing CaO , SiO_2 , Al_2O_3 and small quantities of other materials. The raw meal, paste or suspension must be
20 finely ground, closely mixed and therefore be homogeneous. The clinker of Portland cement used as the starting material for the process of this invention is preferably rich in silicates and contains low percentages of the other oxides.

09890515-073101
TOT E 20-51506860

09890546-073101
TOTAL 57506860

A calcium silicate which can be used as the starting material in the process according to this invention is xonotlite ($\text{Ca}_6\text{Si}_6\text{O}_{17}(\text{OH})_2$) which may be synthesised in hydrothermal conditions according to the following reaction: $\text{CaO}/\text{Ca}(\text{OH})_2 + \text{silica (or sand or quartz)} + \text{H}_2\text{O}$ + minor components (silica fume, bentonite) are made to react in the presence of water vapour at a temperature between 176 and 240°C, at a pressure of 1.4 - 1.5 MPa, for a time of 1 to 24 hours, preferably from 1 to 7 hours, with a molar ratio CaO/SiO_2 between 0.65 and 1 and with a specific surface of the reagents from 18 to 22 m^2 . After cooling, filtration and washing, crystals of xonotlite are obtained.

It is also possible to use as starting material a calcium silicate which may be crystalline or prevalently amorphous. In particular, feeding pure quartz with a diameter < 40 μm , CaO (containing about 7% CaCO_3 , with diameter < 25 μm), silica fume and bentonite in a one-litre stainless steel autoclave, lined, with agitator, and letting it react at a temperature between 195 and 200°C for 24 hours at a pressure of 1.53 MPa, prevalently crystalline calcium silicate is obtained. Instead, using reaction times of 4-7 hours, prevalently amorphous silicates are obtained with a surface area equal to

approximately 100 m²/g.

Another calcium silicate that may be used as a starting material is tobermorite.

The following tables 1 and 2 list some conditions of synthesis of xonotlite (xon-1, xon-2, xon-3) and of amorphous hydrate calcium silicates (CSH-1, CSH-2, CSH-3, CSH-4 and CSH-5) which may be used as starting materials for the procedure according to this invention.

Table 1.

Feed	XON-1	XON-2	XON-3
CaO	55.9%	51.35%	51.3%
SiO ₂	43.9%	48.5%	48.5%
Silica fume	0.2%	0.1%	0.2%
Bentonite	0.05%	0.05%	0.05%
H ₂ O	480%	1200%	1200%
Ca/Si	1.12	0.98	1.00
H ₂ O/dry	4.8	12.00	12.00
Temperature	185°C	195°C	200°C
Pressure	1.1 MPa	1.4 MPa	1.5 MPa
Reaction time	24 h	7 h	4 h
Pressurisation	2.5 h	2.5 h	2.5 h
Depressurisation	6 h	6 h	6 h

ion			
-----	--	--	--

Table 2

Feed	CSH-1	CSH-2	CSH-3	CSH-4	CSH-5
CaO	52.9%	52.9%	48.9%	51.3%	51.3%
SiO ₂	46.8%	46.8%	50.9%	48.5%	48.5%
Silica fume	0.2%	0.2%	0.1%	0.2%	0.2%
Bentonite	0.05%	0.05%	0.05%	0.05%	0.05%
H ₂ O	480%	480%	500%	480%	970%
Ca/Si	1.07	1.07	0.89	1.00	1.00
H ₂ O/dry	4.8	4.8	5.0	4.8	9.7
Temperature	175°C	130°C	197°C	198°C	198°C
Pressure	0.85 MPa	0.3 MPa	1.4 MPa	1.4 MPa	1.4 MPa
Reaction time	7 h	0 h	4 h	2 h	4 h
Pressurisation	2.5 h	1.5 h	2.5 h	2.5 h	2.5 h
Depressurisation	6 h	6 h	6 h	6 h	6 h

5 Figure 1 shows an exemplificative diagram representing a particular embodiment of a system for carrying out the procedure according to this invention.

In the diagram shown in figure 1, 11 indicates the

0959515-02401
TOP SECRET

dissolving reactor, **12** the alumination reactor, **13** the solid-liquid centrifuge, **14** the drier or the precipitation reactor, **15** the washing-drying unit and **16** the mixing unit.

5 According to this diagram, CO₂, xonotlite or calcium silicate and H₂O are loaded at **11** and the dissolution reaction then occurs by acid attack of the silicate; the product obtained arrives at **12** where it is treated with preconstituted solutions of sodium aluminate. At **13**
10 there is then the separation by centrifugation of a solid phase and a liquid phase.

The solid phase, coming from **13**, which by spectroscopic analysis reveals the presence of carbonates, may be sent by means of the mixer **16** to the alumination reactor **12**
15 where it is again treated with sodium aluminate, while the liquid phase is sent to the reactor **14**. The dried/precipitated product arrives at the washing-drying unit **15**, from which the final product, silica, is obtained.

20 The solid phase, coming from **13**, may also be sent back to the dissolution reactor **11**.

The characteristics and the advantages of the procedure according to this invention will be better understood from the following detailed and exemplificative

09890545-033101
TOP SECRET

description.

Example 1A

25 g of (pure) Xonotlite coming from hydrothermal synthesis and having a specific surface BET equal to 54 m²/g were suspended in 400 ml of water (volume H₂O/g of xonotlite = 16) and the suspension was kept in agitation in a one-litre stainless steel autoclave. The reactor was pressurised with CO₂ at 2.0 MPa and the temperature kept at 20°C. The dissolution reaction was made to proceed for 1 hour, up to a pH of about 5.2. The autoclave was then depressurised and the suspension obtained was filtered. The solid obtained from filtration was composed of the mixture of silica and precipitated calcium carbonate, with percentages (of the dry product) of respectively 51.4% and 48.6%.

This mixture was treated with an aqueous solution of sodium aluminate, prepared from NaOH in quantity 1 M and Al in quantity 0.01 M, at environment temperature, under agitation, for 2 hours.

After centrifugation and drying of the supernatant liquid (at pH = 10), a dry residue was obtained (110°C, 4 hours) which on IR analysis revealed an intense and broad absorption at 1015 cm⁻¹, which may be attributed to silicoaluminate entities. The thermal analysis agrees

with the respective spectrophotometric analysis and revealed a high weight loss (about 2.5%) which may be attributed to the loss of free and bonded water ($T \leq 400^{\circ}\text{C}$). The weight loss at $T > 400^{\circ}\text{C}$ is very low (5-10%) and indicates the presence of a low percentage of carbonate and the transformation of the hydroxides present into oxides.

The trend of the curves is very different, for example, from the one that may be obtained analysing the dry residue of the colloidal phase obtained directly after the acid dissolving attack of the phase a).

After treatment of the $\text{CaCO}_3/\text{SiO}_2$ mixture with a solution of sodium aluminate, the solid obtained from drying of the supernatant liquid presented on spectroscopic analysis some absorption bands characteristic of carbonates.

Once washed in water, the IR analysis allowed it to be revealed that these absorption bands were found in the washing waters and no longer in the solid residue, which was therefore silica with high purity.

The precipitated silica obtained after treatment with sodium aluminate is impure with Na_2CO_3 , which is water-soluble and can therefore be removed with washing.

The characterisation of the precipitated silica obtained is shown in the following table 3.

Table 3: Characterisation of precipitated silica (Example 1A).

	• Specific surface BET (m ² /g) 63;
5	• pH (5% aqueous solution) 7;
	• loss at 105°C (%) 4.5%;
	• loss to fire - 1000°C 11.7%;
	• Analysis of the calcinated product at 1000°C for 2 hours:
10	- SiO ₂ (%) 96.5;
	- Al ₂ O ₃ (%) 0.65;
	- Na ₂ O (%) 1.35;
	- CaO (%) 1.4;
	- Fe ₂ O ₃ (%) 0.01

15

The specific surface B.E.T. is determined according to the BRUNAUER-EMMET-TELLER method described in the Journal of the American Chemical Society, vol. 60, page 309, February 1938 and according to standard ISO 9277-95.

20 The pH is determined according to standard ISO 787/9 (pH of a 5% suspension in H₂O).

Example 1B

The solid residue coming from centrifugation in the

previous example 1A was again suspended in water and treated with sodium aluminate and afterwards centrifuged and dried. This further treatment with sodium aluminate allowed a further recover of silica, allowing a possible
5 exhaustion of the silica present in the starting mixture. The characterisation of the precipitated calcium carbonate, obtained after three treatments with sodium aluminate, is shown in the following table 4.

Table 4: Characterisation of precipitated CaCO_3 (Example
10 1B).

- | |
|---|
| <ul style="list-style-type: none">• Specific surface BET (m^2/g) 9;• pH (5% aqueous solution) 10;• loss at 105°C (%) ≤ 2; |
|---|

15 Example 2

A mixture composed of Xonotlite and Tobermorite in weight ratios 70:30 was suspended in water (70 g of mixture in 450 g of water) and the suspension kept in agitation in a one-litre stainless steel autoclave. The reactor was
20 pressurised with CO_2 at 2.0 MPa and the temperature kept at 30°C . The reaction was carried out for 30 minutes, always in agitation, up to a pH of about 5.2. The autoclave was then depressurised and an aqueous solution of sodium aluminate, prepared from NaOH in quantity 3 M

and Al in granules in quantity 0.03 M, was directly added in the reactor. The suspension was kept at environment pressure and temperature, under agitation, for 2 hours. After that period, the suspension in the reactor is centrifuged. Into the liquid, which has a pH value of 11, separated from the solid phase and kept under agitation, CO₂ is bubbled until a pH of 7.5 is reached. The solid and liquid are then separated by filtration. The solid kept back by the filter is washed with deionised water (until a pH of 7 is obtained in the washing water). The solid obtained is composed of precipitated silica with high purity and it has the characteristics listed in table 5.

Example 3

A mixture composed of Xonotlite and Tobermorite is treated substantially following the description in example 2 up to the stage in which the suspension in the reactor is centrifuged. Into the liquid, separated from the solid phase and kept under agitation, CO₂ is bubbled until a pH of 6.5 is reached. The solution gels and is separated by filtration. The gel solid kept back by the filter is washed with deionised water (until a pH of 7 is obtained in the washing water), then dried and crushed. The specific surface BET of the amorphous silica thus

obtained is 90 m²/g:

Table 5: Characterisation of precipitated silica (Example 2).

5	• Specific surface BET (m ² /g) 160;
	• pH (5% aqueous solution) 7;
	• loss at 105°C (%) 4.3;
	• loss to fire - 1000°C (%) 12;
	• Analysis of the calcinated product at 1000°C for 2 hours:
10	- SiO ₂ (%) 97;
	- Al ₂ O ₃ (%) 0.7;
	- Na ₂ O (%) 1.05;
	- CaO (%) 1.24;
	- Fe ₂ O ₃ (%) 0.01
15	

The following examples refer to a number of tests of application.

Example 4

Using the precipitated silica obtained in example 1A, DSP
20 concrete having the following composition was prepared:

- Cement CEM I 52.5 (Ultracem R) 642 g;
- Aggregate: spherical quartz (max. diam. = 1200 g;
3.2 mm)

- Precipitated silica (S.S. BET = 63 m²/g) 80 g;
- Super-fluidifying acrylic additive 44 g;
(Superflux 2000 AC)
- Mixing water 149 g;
- Water/binder* ratio 0.25;
- Aggregate/binder ratio 1.66

* binder = cement + precipitated silica

With this mixture three test pieces with dimensions 40x40x160 mm were prepared and were subjected to accelerated curing (24 hours in water at 80°C).

- 5 The mechanical strength values measured on the test pieces were:

Rc = 119 MPa;

Rf = 18.7 MPa.

Example 5

- 10 A mixture for tyres was prepared containing precipitated silica from example 2.

The specific surface BET of the silica was 160 m²/g.

The mixture was prepared with 40 parts of silica to every 100 parts of styrene butadiene rubber (SBR) and presents

- 15 the following characteristics:

Ultimate elongation = 720%;

Ultimate tensile stress = 16 MPa;

Modulus at 500% = 6.5 MPa.

T01E20"5T506860

So, as previously indicated and shown, the precipitated silica obtained with the procedure according to this invention may be successfully used in high-performance concretes, such as high or very high strength concretes (DSP) or it may be added to mixtures for tyres with low rolling resistance force.

It was also found that both the solid phase 2 and the solution 3 obtained at the end of phase c) of the procedure according to this invention may be used with excellent results as additives in mixtures for tyres and in high performance concretes (for example high or very high strength concretes).

CLAIMS

1. Procedure for preparing amorphous silica comprising the following phases:

a) reaction of a calcium silicate with CO_2 in an aqueous environment with the formation of a suspension **1** of agglomerated particles of SiO_2 and CaCO_3 ;

b) treatment of the suspension **1** with a compound of aluminium, boron or zinc or mixtures of the same in a neutral or basic environment, and formation of a solid phase **2** in a solution **3** containing particles of SiO_2 with nanometric dimensions;

c) separation of the solid phase **2** from the solution **3**;

d) treatment of the solution **3** according to one of the following methods;

e) precipitation or drying;

f) gelation.

2. Procedure according to claim 1, wherein the reaction of phase a) is carried out in an autoclave at a pressure between 0.3 MPa and 3 MPa and at a temperature between 10°C and 100°C .

3. Procedure according to claim 2, wherein the pressure is between 1.0 and 2.5 MPa and the temperature is between 15°C and 40°C .

4. Procedure according to claim 3, wherein the pressure

095055-0310
T01E20-5T506860

is equal to 2 MPa and the temperature is equal to 20°C or 30°C.

5. Procedure according to claim 1, wherein the compound of aluminium, boron or zinc is a salt chosen among
5 aluminates, borates or zincates.

6. Procedure according to claim 5, wherein the salt is an alkaline aluminate or an alkaline earth aluminate

7. Procedure according to claim 5, wherein the salt is a sodium aluminate

10 8. Procedure according to claim 1, wherein the neutral or basic environment is realised using a solution of hydroxides or salts of alkaline metals or alkaline earth metals.

9. Procedure according to claim 8, wherein the solution
15 is an aqueous solution of hydroxides of alkaline metals or alkaline earth metals.

10. Procedure according to claim 8, wherein the solution is an aqueous solution of sodium hydroxide.

11. Procedure according to claim 1, wherein the particles
20 of silica in the solution **3** have dimensions between 1 and 100 nanometers.

12. Procedure according to claim 1, wherein the separation phase c) is carried out by centrifugation.

13. Procedure according to claim 1, wherein the solid

40 30 20 10 0 10 20 30 40 50 60 70 80 90 100

phase 2 coming from the separation phase c) is recycled so as to be again subjected to treatment with sodium aluminate as in phase b).

14. Procedure according to claim 1, wherein the precipitation treatment e) is carried out with the addition of CO₂, at environment pressure and temperature.

15. Procedure according to claim 14, wherein the phases that formed during the precipitation phase are separated by filtration and the solid kept back by the filter is washed until a neutral pH is reached in the washing waters

16. Procedure according to claim 1, wherein the gelation treatment f) is achieved by acidification, for example by adding CO₂, at environment temperature, to a pH lower than 7, and is followed by the evaporation of the liquid phase.


17. Precipitated silica that can be obtained with the procedure according to one of the claims from 1 to 16, characterised by having purity $\geq 96\%$

18. Use of the silica obtained with the procedure according to any one of the claims from 1 to 16 as an additive in mixtures for tyres.

19. Use of the silica obtained with the procedure according to any one of the claims from 1 to 16 as an

09890545-0101

25. Composition of precipitated silica which may be obtained according to the procedure of claim 1.

Fig.1

U1P 3

Docket No: _____

**APPLICATION FOR UNITED STATES LETTERS PATENT
DECLARATION, POWER OF ATTORNEY, AND PETITION**

As a below-named inventor, I declare that:

My residence, post office address and citizenship are as stated next to my name; I believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural inventors are named below) of the invention which is described and which is claimed in the specification, entitled: **PROCEDURE FOR PREPARING SILICA FROM CALCIUM SILICATE**.

The specification [] is attached hereto [X] was filed on **1 FEBRUARY 2000**, as Application Serial No. **PCT/EP00/00757**

I hereby state that I have reviewed and understand the contents of said specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed.¹

COUNTRY	APPLICATION NUMBER	DATE (Day, Month, Year)	PRIORITY CLAIMED UNDER 35 U.S.C. 119	
ITALY	MI99A000197	3 FEBRUARY 1999	Yes [X]	No []
			Yes []	No []

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

¹In Non-Convention cases, a listing of all filings and current status of cases filed more than a year before the U.S. filing is required to comply with 37 CFR 1.56(a). Such a listing may be attached.

APPLICATION SERIAL NO.	FILING DATE	STATUS

I hereby appoint my attorneys with full power of substitution and revocation, to prosecute this application and to transact all business in the U.S. Patent & Trademark Office connected therewith:

Edward A. Hedman, Reg. No. 22,120; Thomas M. Gibson, Reg. No. 24,638; James V. Costigan, Reg. No. 25,669; Kenneth F. Florek, Reg. No. 33,173; Alan B. Clement, Reg. No. 34,563; Martin P. Endres, Reg. No. 35,498 and Timothy X. Gibson, Reg. No. 40,618.

CORRESPONDENCE AND CALLS TO: James V. Costigan, Esq.
HEDMAN, GIBSON & COSTIGAN, P.C.
1185 Avenue of the Americas
New York, NY 10036-2601
Telephone: (212) 302-8989

The undersigned declares further that all statements made herein of his own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

INVENTOR(S)	DATE	RESIDENCE AND P.O. ADDRESS
1-00 Name: Paolo GRONCHI Signature: <i>Paolo Gronchi</i>	Date: 26 JULY 2001 Citizen of: ITALY	Via Solari 2/A I-20144 MILAN, Italy <i>ITX</i>
Name: Tiziana DE MARCO Signature: <i>Tiziana De Marco</i>	Date: 26 JULY 2001 Citizen of: ITALY	Via Lungo Brembo 34 I- 24035 CURNO-BERGAMO Italy
2-00 Name: Luigi CASSAR Signature: <i>Luigi Cassar</i>	Date: 26 JULY 2001 Citizen of: ITALY	Via Europa 42 I-20097 SAN DONATO MILANESE MILAN, Italy <i>ITX</i>
Name: Signature:	Date: Citizen of:	